



Date of Issue: 3/30/2022
 Report Number: 22-001205
 Revision Number: 1
 Date Order Received: 03/21/2022

For the Account of: Camira Fabrics Ltd.
 Meltham Mills
 Meltham
 Holmfirth, West Yorkshire HD9 4AY
 United Kingdom

Client's Identification: Sonus

CERTIFICATE OF TESTING

TEST PERFORMED: Colorfastness to Light AATCC Test Method 16.3-2014, Option 3; CFFA-2 Fadeometer

TEST RESULTS

| | |
|---------------|------------------------|
| Rating | Number of Hours |
| Class 5.0 | 40 |

RATING SYSTEM

- Class 5 No fading or color change
- Class 4 Slight fading or color change
- Class 3 Noticeable fading or color change
- Class 2 Considerable fading or color change
- Class 1 Much fading or color change

NOTES

Light Source: Xenon -Arc, Water Cooled, Continuous Light
Scale Used for Evaluation: AATCC Gray Scale for Color Change

ACCEPTANCE CRITERIA

| | |
|--|----------------------------|
| A.C.T. Standard Woven & Knit Upholstery | Acceptance Criteria |
| Direct Glue Wallcoverings | Class 4 minimum - 40 hours |
| Panels and Upholstered Walls | Class 4 minimum - 40 hours |
| Draperies | Class 4 minimum - 60 hours |

| | |
|--|-----------------------------|
| A.C.T. Standard Coated Fabrics Upholstery | Acceptance Criteria |
| Direct Glue Wallcoverings | Class 4 minimum - 200 hours |
| Panels and Upholstered Walls | Class 4 minimum - 200 hours |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature

Date Order Completed: 03/30/2022



Date of Issue: 3/30/2022
 Report Number: 22-001206
 Revision Number: 1
 Date Order Received: 03/21/2022

For the Account of: Camira Fabrics Ltd.
 Meltham Mills
 Meltham
 Holmfirth, West Yorkshire HD9 4AY
 United Kingdom

Client's Identification: Sonus

CERTIFICATE OF TESTING

TEST PERFORMED: Colorfastness to Light AATCC Test Method 16.3-2014, Option 3; CFFA-2 Fadeometer

TEST RESULTS

| | |
|-----------|-----------------|
| Rating | Number of Hours |
| Class 5.0 | 40 |

RATING SYSTEM

- Class 5 No fading or color change
- Class 4 Slight fading or color change
- Class 3 Noticeable fading or color change
- Class 2 Considerable fading or color change
- Class 1 Much fading or color change

NOTES

Light Source: Xenon -Arc, Water Cooled, Continuous Light
 Scale Used for Evaluation: AATCC Gray Scale for Color Change

ACCEPTANCE CRITERIA

| | |
|---|-----------------------------|
| A.C.T. Standard Woven & Knit | Acceptance Criteria |
| Upholstery | Class 4 minimum - 40 hours |
| Direct Glue Wallcoverings | Class 4 minimum - 40 hours |
| Panels and Upholstered Walls | Class 4 minimum - 40 hours |
| Draperies | Class 4 minimum - 60 hours |
| | |
| A.C.T. Standard Coated Fabrics | Acceptance Criteria |
| Upholstery | Class 4 minimum - 200 hours |
| Direct Glue Wallcoverings | Class 4 minimum - 200 hours |
| Panels and Upholstered Walls | Class 4 minimum - 200 hours |

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Berta Stiver

Authorized Signature

Date Order Completed: 03/30/2022